



*Manufacturers and suppliers of quality
coating systems and associated materials
to the Floor Covering and Building Industries.*

DURON SEAMLESS COATING SYSTEMS

FACT SHEET no. 5

DURON DECORATIVE COLOUR FLAKE APPLICATION:

The Epoxy is cut in with a brush around the edges, and rolled out on the floor in recommended 2 to 3 m² sections at a time, broadcasting flake as you go. Starting from the back wall, lean over the wet epoxy and hand broadcast the flake in an upward and forward direction.

Walk sideways and cast the flake until the basecoat has no visible patches of base colour, approximate coverage of flake: Standard 3.75m² per kilo, Stone Grip 2m² per kilo and Classic XL 5m² per kilo if a full coverage is the desired look.

Ensure you always leave a wet line between you and the already cast flake area. Proceed with the next section and repeat until finished.

DISCLAIMER:

The above information is given in good faith as a suggested guide in the preparation and use of Duron coating systems, no guarantee or warranty is expressed or implied. Any circumstances not covered by this guide should be referred to Duron Pty Ltd or its distributors for any particular attention required. There are however, many factors that may affect the outcome of individual projects using our products that are beyond our control. Duron Pty Ltd cannot be held responsible for poor climatic conditions, inadequate surface preparation, inadequate mixing, poor application techniques, non compliance with curing times, improper thinning of coatings or any other variable beyond our control. No liability will be accepted by Duron Pty Ltd, our employees, distributors, representatives or agents, for any loss or damage, direct or indirect that may result from the use of information and/or suggestions as actual conditions for use that are beyond our control. All materials should be checked and tested for their suitability for prevailing conditions on all individual sites.