



*Manufacturers and suppliers of quality
coating systems and associated materials
to the Floor Covering and Building Industries.*

DURON SEAMLESS COATING SYSTEMS

FACT SHEET no.6

DURON UV STABLE POLYURETHANE (OPTION):

Gloss for 1st and 2nd coat

Or Gloss for 1st coat and Satin for Final coat only

Ensure the basecoat and flake surface is completely dry (approximately 6-8 hours). Scrape dry Flake with a Floor Scraper (for Stone Grip use a stiff broom) in a north-south and east-west direction to dislodge all unsecured flake, vacuum thoroughly to remove all excess loose flake. The floor is now ready for the 1st coat of DURON UV Stable Gloss Polyurethane.

Application (1st Coat): Apply 1st coat of polyurethane with a 10mm nap micro fibre roller cover and brush for edges, at a coverage Rate: 1 Litre to cover 4-5m² for the first coat, ensuring an even saturation with no puddles, allow to dry for 6-8 hours.

Application (2nd coat): Light sand to take of any sharp edges, vacuum and apply second coat of polyurethane with a 10mm nap micro fibre roller cover and brush for edges at a coverage rate: 1 Litre to cover 6-7 m² for the second coat ensuring an even saturation with no puddles.

NOTE: SATIN UV Stable Polyurethane is available and an option for a FINAL COAT ONLY.

DISCLAIMER:

The above information is given in good faith as a suggested guide in the preparation and use of Duron coating systems, no guarantee or warranty is expressed or implied. Any circumstances not covered by this guide should be referred to Duron Pty Ltd or its distributors for any particular attention required. There are however, many factors that may affect the outcome of individual projects using our products that are beyond our control. Duron Pty Ltd cannot be held responsible for poor climatic conditions, inadequate surface preparation, inadequate mixing, poor application techniques, non compliance with curing times, improper thinning of coatings or any other variable beyond our control. No liability will be accepted by Duron Pty Ltd, our employees, distributors, representatives or agents, for any loss or damage, direct or indirect that may result from the use of information and/or suggestions as actual conditions for use that are beyond our control. All materials should be checked and tested for their suitability for prevailing conditions on all individual sites.