



*Manufacturers and suppliers of quality  
coating systems and associated materials  
to the Floor Covering and Building Industries.*

## DURON SEAMLESS COATING SYSTEMS

### FACT SHEET No. (6) a

#### **DURON POLYASPARTIC UV STABLE GLOSS (OPTION):**

Ensure the basecoat and flake surface is completely dry (approximately 6-8 hours). Scrape dry Flake with a Floor Scraper (for Stonegrip use a stiff broom) in a north-south and east-west direction to dislodge all unsecured flake, vacuum thoroughly to remove all loose excess flake. The floor is now ready for the top coat of Duron Polyaspartic.

**Application (Topcoat):** Apply coating of Duron Polyaspartic with a 10mm nap micro fibre roller cover and brush all edges, at a coverage Rate: 1 Litre to cover 5m<sup>2</sup> for this coat, (mixing ratio: 1L A to 1L B) ensuring an even saturation with no puddles, allow to cure approximately 3-4 hours.

**Please refer to Duron Polyaspartic TDS before application\***

#### DISCLAIMER:

The above information is given in good faith as a suggested guide in the preparation and use of Duron coating systems, no guarantee or warranty is expressed or implied. Any circumstances not covered by this guide should be referred to Duron Pty Ltd or its distributors for any particular attention required. There are however, many factors that may affect the outcome of individual projects using our products that are beyond our control. Duron Pty Ltd cannot be held responsible for poor climatic conditions, inadequate surface preparation, inadequate mixing, poor application techniques, noncompliance with curing times, improper thinning of coatings or any other variable beyond our control. No liability will be accepted by Duron Pty Ltd, our employees, distributors, representatives or agents, for any loss or damage, direct or indirect that may result from the use of information and/or suggestions as actual conditions for use that are beyond our control. All materials should be checked and tested for their suitability for prevailing conditions on all individual sites.